Q 20-885 | Polyester Repair Resin

Characteristics

20-885 is a fast curing polyester based laminating resin. In combination with fiberglass it is a high performance system to repair easily and quickly larger holes in GRP parts and car body sheets. In order to achieve good sanding results, it is recommended to apply 1 thin layer of putty, after the resin is fully cured.

Physical Characteristics

PE: Polyester	VOC: 2004/42/IIB(b)(250)<250
COLOR:	12 M: 12 month

Mixing

100:2-3	20°C 10 min

Drying

	20°C	60°C			
	30 min	15 min	P80-P240	P80-P240	n/a

Storage

Store the product in a ventilated place. Keep away from direct exposure to sunlight.
Keep between +5°C and 20°C.

Safety

For more informations check the safety data sheet.

This data sheet is for information purpose only. To our knowledge the data provided complies with the latest standard and is based on years of experience in the manufacturing of our products.
Copyright: ColorCompany GmbH, all rights reserved.

Version: 14-04-2026

ColorCompany GmbH • Kadener Straße 9 • D-25486 Alveslohe, Germany
+49 (0) 4192 89142 0 • www.color-company.com • info@color-company.com