

# Technical Data Sheet



Peter Kwasny GmbH, Heilbronner Str. 96  
74831 Gundelsheim / Germany  
Phone: +496269 95-0, Fax: +496269 95-80  
www.spraymax.com / www.kwasny.com / info@kwasny.de

## SprayMax® 1K Primer Filler - Primer Shade white 400 ml Art. Nr. 680271



### Product

#### Description / Purpose

1K Primer Shades form a system of 1K filler primers in grey tones ranging from white to black. By selecting a primer colour that matches the brightness of the following base coat the coverage of the base coat will be increased.

#### Properties

- Excellent adhesion, high anti-corrosion properties
- Can be used as a primer or filler
- Can be topcoated with a water borne or solvent borne paint.
- Wet-on-wet processing possible
- Smooth running, fast drying

#### Material base

Polyvinyl butyral resins, epoxy resins

#### Colour

White

#### VOC Value (EU)

575 g/l

### Substrate

Steel (cleaned and sanded)

Galvanised steel (hot-galvanised, strip galvanised and electro-galvanised cleaned and sanded)

Aluminium, soft aluminium (cleaned and sanded)

FRP materials (cleaned and sanded)  
 Polyester surfaces (cleaned and sanded)  
 E-coat (cleaned and sanded)  
 Old paint and factory paint (cleaned and sanded)

The damaged area must be dry and free of grease and dust and all rust needs to be removed.


## Processing

### Protection measures




Wear personal protection equipment.  
 (respiratory mask/gloves/goggles)  
 For more information, see safety data sheet.

### Shake




Shake can thoroughly for at least 2 minutes from when the mixing balls are heard.

### Adjustable Nozzle




Set the variable spray nozzle to the size and pattern of the damage.

### Spray to test




After shaking the can, test spray and check compatibility with the surface and the colour.

### Spraying distance




15 cm - 20 cm

### Spray passes




1 - 3 spray coats each approx 15 µm  
Wash primer: 1 spray coat, Primer: 1 - 2 spray coats,  
Primer filler: 2 - 3 spray coats

### Flash-off time




Flash time:  
 approx. 3 - 5 min between each spray coat

### Processing conditions




Optimum application at 18° C - 25° C and a relative humidity from 40 - 60 %.

## Coverage



approx. 4 - 5 m<sup>2</sup> at approx. 10 - 15 µm  
 approx. 2 m<sup>2</sup> at approx. 25 µm  
 dry film thickness

## Drying




TG1 dust dry: 10 - 12 min  
 TG3 dry to touch: approx. 15 min  
 Ready for sanding: approx. 25 min  
 The stated values refer to the above mentioned processing conditions. The level of dryness is determined pursuant to DIN 53150.




IR: 5 - 8 min.  
 Observe equipment description

## Continue

SprayMax® 1K filler primer Primer Shades can be top coated with conventional fillers, top coats, base coats and water-based coats. Can be processed wet-on-wet after a flash-off time of 15 - 30 min.




dry sanding with P 360 - P 500



Wet sanding with P 800 - P 1200 or  
 dry sanding with P 400 - P 500

## Finish



After painting, turn the can upside down and spray the valve until empty.

## Additional Information


### Important Information



Avoid bumps, friction and impact.

Do not topcoat with polyester and EP products.  
 SprayMax® 1K primer filler Primer Shades have an outdoor shelf life on steel of 3 months; a dry film layer of 50 µm should not be undercut.

## Shelf Life



60 months

The usage period refers to an unused can that is stored correctly at a temperature of 15 - 25° C and a relative humidity below 60%. The can must be stored and transported in an upright position in a dry place where it is protected against chemical and mechanical influences. The safety information on the can and all statutory provisions applicable for the storage site must be observed.

## Disposal



The completely emptied spray cans must be disposed of in the recycling system. Cans with hardened material must be disposed of as special waste.

## Note

For professional use only.

Identification, see safety data sheet.

The contents in this technical data sheet were created with great care and reflect our current state of knowledge. They provide the user with application-specific information and do not promise certain properties. The information is non-binding and we accept no liability for its integrity, accuracy and completeness. They do not relieve the user of their duty to check the suitability of our product for the intended purpose. The warnings printed on our labels must be respected. Our brands and patents are protected by copyright. All rights reserved We reserve the right to update, amend or supplement the content of the information without prior notice.