### Art.Nr. 680276

### Version 9/2024

### Page 1

Peter Kwasny GmbH, Heilbronner Str. 96 74831 Gundelsheim / Germany Phone: +496269 95-0, Fax: +496269 95-80 www.spraymax.com / www.kwasny.com / info@kwasny.de

**Technical Data Sheet** 

## **SprayMax**®

1K Primer Filler - Primer Shade dark grey 400 ml Art. Nr. 680276

## **Product**

Description / Purpose	1K Primer Shades form a system of 1K filler primers in grey tones ranging from white to black. By selecting a primer colour that matches the brightness of the following base coat the coverage of the base coat will be increased.
Properties	<ul> <li>Excellent adhesion, high anti-corrosion properties</li> <li>Can be used as a primer or filler</li> <li>Can be topcoated with a water borne or solvent borne paint.</li> <li>Wet-on-wet processing possible</li> <li>Smooth running, fast drying</li> </ul>
Material base	Polyvinyl butyral resins, epoxy resins
Colour	Dark grey
VOC Value (EU)	575 g/l
<u>Substrate</u>	
	Steel (cleaned and sanded)
	Galvanised steel (hot-galvanised, strip galvanised
	and electro-galvanised cleaned and sanded)
	Aluminium, soft aluminium (cleaned and sanded)
	FRP materials (cleaned and sanded)
	Polyester surfaces (cleaned and sanded)







E-coat (cleaned and sanded)

Old paint and factory paint (cleaned and sanded) The damaged area must be dry and free of grease and dust and all rust needs to be removed.

## **Processing**

ribecoonig		
Protection measures	$\bigcirc$	Wear personal protection equipment.
		(respiratory mask/gloves/goggles)
	060	For more information, see safety data sheet.
Shake		Shake can thoroughly for at least 2 minutes from
		when the mixing balls are heard.
Adjustable Nozzle		Set the variable spray nozzle to the size and
		pattern of the damage.
Spray to test		After shaking the can, test spray and check
		compatibility with the surface and the colour.
Spraying distance		15 cm - 20 cm
	<b>┥</b>	
Spray passes		1 - 3 spray coats each approx 15 μm
		Wash primer: 1 spray coat, Primer: 1 - 2 spray coats,
		Primer filler: 2 - 3 spray coats
Flash-off time		Flash time:
	$ \langle \uparrow \langle \uparrow \langle  $	approx. 3 - 5 min between each spray coat
Processing conditions		Optimum application at 18° C - 25° C and a relative
		humidity from 40 - 60 %.
Coverage		approx. 4 - 5 m² at approx. 10 - 15 µm
		approx. 2 m² at approx. 25 μm

dry film thickness



## Drying



TG1 dust dry: 10 - 12 min TG3 dry to touch: approx. 15 min Ready for sanding: approx. 25 min

The stated values refer to the above mentioned processing conditions. The level of dryness is determined pursuant to DIN 53150.



IR: 5 - 8 min. Observe equipment description

SprayMax® 1K filler primer Primer Shades can be top coated with conventional fillers, top coats, base coats and water-based coats. Can be processed wet-on-wet after a flash-off time of 15 - 30 min.



dry sanding with P 360 - P 500



Wet sanding with P 800 - P 1200 or dry sanding with P 400 - P 500



After painting, turn the can upside down and spray for 3 - 5 seconds to clean the valve.

Finish

# **Additional Information**

**Important Information** 



Avoid bumps, friction and impact.

Do not topcoat with polyester and EP products. SprayMax® 1K primer filler Primer Shades have an outdoor shelf life on steel of 3 months; a dry film layer of 50 µm should not be undercut.

## Continue



### Shelf Life



#### 60 months

The usage period refers to an unused can that is stored correctly at a temperature of 15 - 25° C and a relative humidity below 60%. The can must be stored and transported in an upright position in a dry place where it is protected against chemical and mechanical influences. The safety information on the can and all statutory provisions applicable for the storage site must be observed.

### Disposal

Note

The completely emptied spray cans must be disposed of in the recycling system. Cans with hardened material must be disposed of as special waste.

For professional use only. For labelling see safety data sheet.

The contents in this technical data sheet were created with great care and reflect our current state of knowledge. They provide the user with application-specific information and do not promise certain properties. The information is non-binding and we accept no liability for its integrity, accuracy and completeness. They do not relieve the user of their duty to check the suitability of our product for the intended purpose. The warnings printed on our labels must be respected. Our brands and patents are protected by copyright. All rights reserved We reserve the right to update, amend or supplement the content of the information without prior notice.